

GENERAL INFORMATION
General information

Color	White nickel-free
Color shade	Off-white
Typology	Master alloy for gold
Production process	Casting

Melting temperatures

Solidus [°C]	910.0
Melting range [°C]	90.0
Liquidus [°C]	1000.0

Commercial composition

Silver (%)	35,00
Copper (%)	26,00
Palladium (%)	31,00
Zinc (%)	8,00



Proderma

FULL CHARACTERIZATION DATA
Color coordinates

L*	81.3
a*	3.2
b*	13.4
c*	13.7
Yellow index	29.8

General characteristics

As cast grain size [µm]	22
-------------------------	----

Mechanical characteristics

As cast hardness [HV 0.2]	155.0
Hardness after annealing [HV 0.2]	155.0
Hardness after 70% area red. [HV 0.2]	260.0
Single step age-hardening hardness [HV 0.2]	215.0
Tensile strength (Rm) [Mpa]	485.0
Yield strength (Rp0.2) [MPa]	278.0
Elongation at rupture (A) [%]	29.0

Product applications

Casting in closed systems
Casting in open systems
Casting without stones

CASTING PROCESSING PARAMETERS

Pre-mixing temperature [°C] 1125.0

CASTING TEMPERATURES	Flask from [°C]	Flask to [°C]	Metal from [°C]	Metal to [°C]
< 0.5 mm	660.0	720.0	1100.0	1130.0
0.5 - 1.2 mm	580.0	650.0	1080.0	1100.0
> 1.2 mm	460.0	600.0	1060.0	1080.0

Trees without stones

Let the flask cool down for 10-15 minutes, then quench in water.

Stone-in-place casting trees

Let the flask cool down for 45-60 minutes, then quench in water.

Pickling

Dip in RADIAL solution (50 g/l conc. at 60°C for 5-10 min.), or in sulphuric acid (10% conc. at 50°C for 10 min.)