

GENERAL INFORMATION
General information

Typology	Master alloy for gold
Color	Yellow
Color shade	Rich yellow
Production process	All-purpose
Grain refinement level	Medium
Deoxidation level	Minimum

Commercial composition (%)

CU	51.0
AG	49.0

Melting Temperatures

Solidus [°C]	875.0
Liquidus [°C]	900.0
Melting range [°C]	25.0

FULL CHARACTERIZATION DATA
Color coordinates

L *	a*	b*	c*	Yellow Index
86.0	5.3	23.8	24.4	

Mechanical characteristics

As cast hardness [HV 0.2]	140.0
Hardness after 70% area red. [HV 0.2]	250.0
Hardness after annealing [HV 0.2]	155.0
Single step age-hardening hardness [HV 0.2]	245.0
Tensile strength (Rm) [Mpa]	427.0
Yield strength (Rp0.2) [MPa]	298.0
Elongation at rupture (A) [%]	42.0

Physical characteristics

Density [g/cm ³]	15.2
------------------------------	------

General characteristics

As cast grain size [μm]	150.0
-------------------------	-------

Product applications

Continuous casting
 Ingot casting
 Casting in closed systems
 Casting without stones
 Handmade production
 Massive chain production
 Wire production
 Sheet production
 Stamping production
 Age hardening

A183N 750‰

ALL-PURPOSE MASTER ALLOY FOR 750‰ (18 KT) YELLOW GOLD

CASTING PROCESSING PARAMETERS

POURING TEMPERATURES	Flask from [°C]	Flask to [°C]	Metal from [°C]	Metal to [°C]
< 0.5 mm	660	720	1000	1030
0.5 - 1.2 mm	580	650	980	1000
> 1.2 mm	460	600	960	980

Trees without stones

Let the flask cool down for 10-15 minutes, then quench it in water.

Stone-in-place casting trees

Let the flask cool down for 30-45 minutes, then quench it in water.

Pickling

Dip in RADIAL solution (50 g/l conc. at 60°C) for 2 minutes, or in sulphuric acid (10% concentration at 50°C) for 5 minutes.

MECHANICAL WORKING PARAMETERS
Reductions

Wire - diameter (%)	45.0
Sheet - area or thickness (%)	70.0

POURING TEMPERATURES	Countinous from [°C]	Countinous to [°C]	Ingot to [°C]	Ingot from [°C]
Temperatures	1000	1080	980	1020

MECHANICAL WORKING ANNEALING	Temp. from [°C]	Temp. to [°C]	Time [min]
< 1 mm	620	660	25
1 - 5 mm	620	660	30
> 5 mm	620	660	35

Mechanical working quenching

Quench directly in water.

AGE HARDENING PROCESSING PARAMETERS

SINGLE STEP	Temperature [°C]	Time [min]	Quenching
AGE HARDENING	275.0	90.0	In air or in furnace