

**GENERAL INFORMATION**
**General information**

Typology	Master alloy for gold
Color	Yellow
Color shade	Rich yellow
Production process	Casting
Grain refinement level	Low
Deoxidation level	Medium

**Commercial composition (%)**

CU	71.0
ZN	17.0
AG	12.0

**Melting Temperatures**

Solidus [°C]	820.0
Liquidus [°C]	875.0
Melting range [°C]	55.0

**FULL CHARACTERIZATION DATA**
**Color coordinates**

L *	a*	b*	c*	Yellow Index
85.7	2.7	18.0	18.2	

**Mechanical characteristics**

As cast hardness [HV 0.2]	120.0
Hardness after 70% area red. [HV 0.2]	250.0
Hardness after annealing [HV 0.2]	135.0
Single step age-hardening hardness [HV 0.2]	120.0
Tensile strength (Rm) [Mpa]	447.0
Yield strength (Rp0.2) [MPa]	242.0
Elongation at rupture (A) [%]	33.0

**Physical characteristics**

Density [g/cm³]	12.8
-----------------	------

**General characteristics**

As cast grain size [µm]	330.0
-------------------------	-------

**Product applications**

Stone-in-place casting  
Casting in closed systems  
Casting without stones

**CASTING PROCESSING PARAMETERS**
**Pre-melting temperature**

Temperature [°C] 995

**POURING TEMPERATURES**

	Flask from [°C]	Flask to [°C]	Metal from [°C]	Metal to [°C]
< 0.5 mm	660	720	975	1005
> 1.2 mm	460	600	935	955
0.5 - 1.2 mm	580	650	955	975

**Trees without stones**

Let the flask cool down for 10-15 minutes, then quench it in water.

**Stone-in-place casting trees**

Let the flask cool down for 30-45 minutes, then quench it in water.

**Pickling**

Dip in RADIAL solution (50 g/l conc. at 60°C) for 2 minutes, or in sulphuric acid (10% concentration at 50°C) for 5 minutes.

**AGE HARDENING PROCESSING PARAMETERS**

SINGLE STEP	Temperature [°C]	Time [min]	Quenching
-------------	------------------	------------	-----------

**AGE HARDENING**