

**MASTER  
ALLOY**
**LSG419 585‰**

MASTER ALLOY FOR SOLDERING OF 375‰ (9KT) YELLOW GOLD

**GENERAL INFORMATION**
**General information**

Typology	Gold solder
Color	Yellow
Color shade	Greenish yellow
Production process	Brazing
Grain refinement level	Minimum
Deoxidation level	Minimum

**Commercial composition (%)**

AG	50.0
CU	28.0
ZN	15.0
IN	7.0

**Melting Temperatures**

Solidus [°C]	680.0
Liquidus [°C]	735.0
Melting range [°C]	55.0

**FULL CHARACTERIZATION DATA**
**Color coordinates**

L *	a*	b*	c*	Yellow Index
91.6	-1.2	16.9	16.9	

**Mechanical characteristics**

As cast hardness [HV 0.2]	195.0
---------------------------	-------

**Physical characteristics**

Density [g/cm <sup>3</sup> ]	12.2
------------------------------	------

**Product applications**

**MECHANICAL WORKING PARAMETERS**
**Pre-melting temperature**

Temperature [°C] 855

**Reductions**

Wire - diameter (%)	15.0
Sheet - area or thickness (%)	40.0

**POURING TEMPERATURES**

Countinous from [°C]

Countinous to [°C]

Ingot to [°C]

Ingot from [°C]

Temperatures

835

915

815

855

**MECHANICAL WORKING ANNEALING**

Temp. from [°C]

Temp. to [°C]

Time [min]

&lt; 1 mm

520

550

20

&gt; 5 mm

520

550

25

1 - 5 mm

520

550

30

**Mechanical working quenching**

Quench directly in water.

**LSG419 585‰**

MASTER ALLOY FOR SOLDERING OF 375‰ (9KT) YELLOW GOLD

**Preliminary checks**

Please note that in order to correctly evaluate the alloy's hardness to solderability, it is advised to make a numerical calculation by subtracting the base metal solidus temperature value from the solder liquidus temperature value. The higher the number resulting, the more solderable (or the less hard) the alloy can be considered. Please refer to the technical guideline for solders available in the website for further information.