

GENERAL INFORMATION
General information

Production process	Universal
Color	Silver
Typology	Master alloy for silver

Melting temperatures

Liquidus [°C]	900.0
Solidus [°C]	750.0
Melting range [°C]	150.0

Commercial composition

Copper (%)	70,00
Zinc (%)	30,00



SILVER line

FULL CHARACTERIZATION DATA
Color coordinates

L*	92.5
a*	-0.1
b*	5.6
c*	5.6
Yellow index	11.5

General characteristics

As cast grain size [µm]	700.0
-------------------------	-------

Mechanical characteristics

As cast hardness [HV 0.2]	60.0
Hardness after annealing [HV 0.2]	70.0
Hardness after 70% area red. [HV 0.2]	160.0
Single step age-hardening hardness [HV 0.2]	90.0
Double step age-hardening hardness [HV 0.2]	130.0
Tensile strength (Rm) [Mpa]	253.0
Yield strength (Rp0.2) [MPa]	134.0
Elongation at rupture (A) [%]	27.0

Product applications

Stone-in-place casting
Casting in closed systems
Casting without stones

CASTING PROCESSING PARAMETERS

Pre-mixing temperature [°C] 1015.0

CASTING TEMPERATURES	Flask from [°C]	Flask to [°C]	Metal from [°C]	Metal to [°C]
< 0.5 mm	560.0	600.0	1000.0	1030.0
0.5 - 1.2 mm	520.0	560.0	980.0	1000.0
> 1.2 mm	480.0	520.0	960.0	980.0

Trees without stones

Let the flask cool down for 5 minutes, then quench in water.

Stone-in-place casting trees

Let the flask cool down for 30-45 minutes, then quench in water.

Pickling

Dip in RADIAL solution (50 g/l conc. at 60°C for 2 min.), or in sulphuric acid (10% conc. at 50°C for 5 min.)

AGE HARDENING PROCESSING PARAMETERS

SINGLE STEP AGE-HARDENING TREATMENT	Temperature [°C]	Time [min]	Quenching
Age-hardening	300.0	90.0	Air or in furnace

DOUBLE STEP AGE-HARDENING TREATMENT	Temperature [°C]	Time [min]	Quenching
Solubilization	710.0	40.0	Water, immediate
Age-hardening	300.0	60.0	Air or in furnace